



Q. S. ABRASIVI MARENGO S. R. L.
S.S. 35/Bis dei Giovi - Via delle Ghiare
Zona ind. le
15062 BOSCO MARENGO (AL)
c.f.:13089420155
p.iva.: 01899340069
Tel. 0039 0131/298453 Fax. 0039 0131/298457

CHEMICAL ANALISYS



CORINDONE RIGENERATO - ANALISI CHIMICA

<i>Perdita alla calcinazione</i>	<i>0,16%</i>
<i>MnO</i>	<i>0,075%</i>
<i>Zr</i>	<i>0,7%</i>
<i>Na₂O + K₂O</i>	<i>0,12%</i>
<i>Al₂O₃</i>	<i>91-93%</i>
<i>Fe₂O₃</i>	<i>2%</i>
<i>TiO₂</i>	<i>0,6%</i>
<i>CaO</i>	<i>0,16%</i>
<i>SiO₂</i>	<i>1,68%</i>
<i>MgO</i>	<i>0.2%</i>

Peso Specifico: **3,90 g/cm³**

Durezza: **Knoop 1800, Mohs 9**

Punto Fusione: **2040°C**

Q.S.Abrasivi Marengo SRL
Querini Leonardo
Sales Manager
vendite@qsabrasivi.com